

## TEROSON® MS 9320 SF 2C

February 2025

### Product description

TEROSON® MS 9320 SF 2C provides the following product characteristics:

<b>Technology</b>	Silane-modified polymer
<b>Product type</b>	Adhesive/Sealant
<b>Components</b>	Two-component
<b>Cure</b>	Cure at ambient temperature
<b>Appearance (Component A)</b>	grey
<b>Appearance (Component B)</b>	white
<b>Consistency</b>	Low viscous, Thixotropic
<b>Odor</b>	Characteristic
<b>Mix ratio, by volume (Component A : B)</b>	10:1

TEROSON® MS 9320 SF 2C is a low viscosity two-component adhesive based on silane modified polymers which cures to an elastic product. It can be applied in beads or sprayed out of the cartridge. The material is free of solvents, isocyanates and silicones.

It displays following properties:

- Very fast cure
- Sprayable and brushable
- Thixotropic after application
- Primerless adhesion in most cases
- Paintable up to three days after application
- Spotweldable in uncured state
- UV resistant
- High ageing resistance

### Application areas

TEROSON® MS 9320 SF 2C covers a various range of applications in the automotive E-Mobility industrie vehicles and in the repair shop.

Following applications in particular are targeted:

- Bonding of the floor cover
- Bonding of insulation panels
- Low viscosity sealing
- Coating
- Potting

### Technical data

Component A, density, g/cm <sup>3</sup>	approx. 1.55
Component B, density, g/cm <sup>3</sup>	approx. 1.34

### Mixture (Component A+B)

Pot life, min*	approx. 5 to 7
Open time, min*	approx. 25
Shore-A-hardness, ISO 868, Durometer A	approx. 25 to 30
Tensile strength, ISO 37, MPa	approx. 1.4
Elongation at break, acc. to ISO 37, speed 200 mm/min, %	approx. 320
Tensile shear strength, acc. to EN 1465, speed 50 mm/min, on 1 mm aluminum, 1 mm layer thickness, MPa	approx. 1.2
Handling time *, acc. to EN 1465, to reach 50	60 to 70
Application temperature, °C	15 to 40
In service temperature range, °C	-40 to 90
* ISO 291 standard climate	23°C, 50%, relative air humidity

### Direction for use

#### Preliminary statement

Prior to use it is necessary to read the **Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

#### Pre-Treatment

The substrates must be clean, dry, oil- and grease free. Cleaners Teroson PU 8550 or Teroson VR 10 are recommended for this. Depending on the surface it can be necessary to roughen the surface or to use an adhesion promoter e.g. Teroson® SB 450 to provide best adhesion. When manufacturing plastics, external release agents are often used; these agents must be accurately removed first. Due to the different compositions of paints, especially powderpaints and the large number of different substrates, application trials before use are necessary.

#### Application

TEROSON® MS 9320 SF 2C consists of two components A and B. By means of suitable application equipment, both A and B component are dosed in a ratio by volume of 10:1 and are homogenously mixed by use of static mixer shortly before application. The adhesive can be applied in beads or sprayed by means of a secondary air connection on the mixer tip. Low material temperatures of the sealant will lead to an increase of viscosity with an impact on the extrusion rate and the spray pattern. The temperature also influences the pot life, open time and cure time. Therefore the product should always be applied in the recommended temperature range. This can be achieved by bringing the adhesive up to room temperature prior to application or storing under controlled temperature.

**Application equipment**

To apply the product correctly, a pneumatic hand gun e.g. 2693825 has to be used. An adapter for the secondary air supply can be provided by Henkel technical customer service. Manual hand guns are not suitable for this product.

**Classification**

Please refer to the corresponding **Safety Data Sheet** for details on:

- Hazards identification**
- Transport information**
- Regulatory information**

**Storage**

Frost-sensitive	no
Recommended storage temperature, °C	10 to 25
Shelf-life (in unopened original packaging), months	12

**Disclaimer**

The information provided in this Technical data sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical data sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 3